TECHNICAL DATA SHEET



V04/06 - 2022

MULTI GREEN PLUS 1.0 SUPER LIGHT

polyester multifuncional putty - green

CHARAKTERISTICS

Multi Green Plus 1.0 Super Light is a superlight polyester putty of the latest generation.

- Latest filling material technology
- Super light
- Set thixotropics
- Very easy to apply
- Pore-free filler
- Approx. 20% faster drying
- Perfect sanding already from grain P150
- Highly surface dry
- Up to 30% higher cutting colume compared to other putties
- Adhesion to galvanized sheet steel
- Adhesion to aluminium and steel surfaces
- Adhesion to wood
- Adhesion to polyester laminates

APPLICATION

For filling deep uneven areas and dents on motor vehicles panels in cars, trucks and railway carriages. Applicable as filling and fine putty.

PRODUCT DATA

MATERIAL DATA:

- delivery viscosity at 20°C: paste-like

- **VOC** - **content**: 2004/42/IIB (b) (250) < 220g/l

- Colour: green

HANDLING

BASE:

The surface must be clean, dry and grease-free. Good adhesion is achieved on all coarsely sanded surfaces.

DOSAGE:

Addition of 2-3% by weight hardener paste

An overdosing of the hardener paste must be avoided. Bleeding through and colour changes in the topcoat system may occur.

 VOSSCHEMIE
 GMBH
 Telefon
 +49 (0) 4122 / 717 -0
 www.carsystem.org

 Esinger Steinweg
 50
 Telefax
 +49 (0) 4122 / 717 -158
 www.vosschemie.de

a trademark of **VOSSCHEMIE**

D – 25436 Uetersen E-Mail info @ vosschemie.de

TECHNICAL DATA SHEET



V04/06 - 2022

POT LIFE:

At +20°C ambient temperature, 12 minutes

REACTION TEMPERATURE:

At least +5°C

APPLICATION:

Spread on with spatula

DRYING TIME:

Air drying at +20°C ambient temperature, 12 minutes

SANDING:

Following the specified drying time.

As filling putty

First sanding - dry with P120 - P240 Re-sanding - dry with P240 - P320

As fine putty

First sanding – dry with P150 – P240 Re-sanding – dry with P240 – P320

REWORKING:

The Multi Green Plus 1.0 Super light can be worked over with the following CS products:

- Elastic green, Elastic weiss, Elastic beige, or with all common 2K Acrylic fillers available on the market.

STORAGE:

Approx. 6 – 8 months at 18 - 20° C in closed original container.

SAFETY ISSUES

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.

Copyright VOSSCHEMIE

